

TEKASTER™ F615G30FR

Polyethylene Terephthalate
Mando Advanced Materials Co., Ltd.

Message:

F615G30FR is GF30% reinforced polyethylene terephthalate (PET). F615G30FR has good properties with flammability UL94 V_0

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.67	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30 to 0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	147	MPa	ASTM D638
Tensile Elongation ² (Break)	2.3	%	ASTM D638
Flexural Modulus ³	10100	MPa	ASTM D790
Flexural Strength ⁴	226	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	78	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	246	°C	
1.8 MPa, Unannealed	224	°C	
Flammability	Nominal Value	Test Method	
Flame Rating	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	4.0 to 5.0	hr	
Rear Temperature	245 to 255	°C	
Middle Temperature	250 to 260	°C	
Front Temperature	255 to 265	°C	
Nozzle Temperature	255 to 265	°C	
Processing (Melt) Temp	255 to 265	°C	
Mold Temperature	80.0 to 100	°C	
NOTE			
1.	5.0 mm/min		
2.	5.0 mm/min		
3.	3.0 mm/min		
4.	3.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

