

Integra™ ABS 6035 GP

Acrylonitrile Butadiene Styrene

PolySource, LLC

Message:

General Purpose, High Flow ABS

General Information			
Features	High liquidity		
	General		
Uses	General		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	34	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 - 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C, 6.35 mm)	102		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	45.0	MPa	ASTM D638
Flexural Modulus (23°C)	2350	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	65.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm)	240	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.35mm	88.9	°C	ASTM D648
1.8 MPa, unannealed, 6.35mm	75.0	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80	°C	
Drying Time	2.0 - 4.0	hr	
Processing (Melt) Temp	220 - 260	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

