

Sinvicomp SIC3704BUV

Rigid Polyvinyl Chloride

Teknor Apex Asia Pacific PTE. LTD.

Message:

"Sinvicomp" SIC 3704BUV is an extrusion grade polyvinylchloride compound available in pellet form. SIC 3704BUV provides medium impact performance suitable for transparent profiles that need reasonable UV resistance.

General Information			
Features	Medium impact resistance		
Uses	Label		
	Hard packaging		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	35.0	MPa	ASTM D638
Tensile Elongation (Break)	150	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	75.0	°C	ASTM D1525
Additional Information			

Typical temperature profile for processing SINVICOMP compound is from 160°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP. Feeding zone: 160°C Compression zone: 160°C~170°C Mixing zone: 170°C~180°C Nozzle/Die Zone: 180°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT