

NORYL™ WCD801AU resin

Polyphenylene Ether + TPE

SABIC Innovative Plastics Asia Pacific

Message:

Flexible, UV stabilized, halogen free extrusion grade for applications such as wire insulation and cable jacket. Good color stability after UV weathering per ASTM D4459. Light color capable. Flame retardant performance capable of meeting UL VW-1 requirement. 80C application temperature rating and good heat deformation performance as defined by UL 1581. 82 Shore A hardness. Processing typically conducted on standard extrusion equipment. UL 1581 tests conducted on 2.0 mm wire with 0.12 mm x 20 stranded copper conductor.

General Information			
Additive	UV stabilizer		
Features	Good flexibility		
	Good color stability		
	Heat resistance, medium		
	Halogen-free		
	Flame retardancy		
Uses	Cable sheath		
	Wire and cable applications		
	Insulating material		
Processing Method	Extrusion coating		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.09 - 1.17	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/5.0 kg)	20	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 30 sec)	82		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Fracture	20.0	MPa	UL 1581
Fracture ¹	15.0	MPa	ASTM D638
Fracture, 113°C ²	21.0	MPa	UL 1581
Fracture	13.0	MPa	ISO 527-2/50
Tensile Elongation			
Fracture	260	%	UL 1581
Fracture ³	160	%	ASTM D638
Fracture, 113°C ⁴	210	%	UL 1581
Fracture	110	%	ISO 527-2/50
Flexural Modulus ⁵			
100mm span	130	MPa	ASTM D790
--	115	MPa	ISO 178

Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -40.0	°C	ASTM D746
UL Temperature Rating	80	°C	UL 1581
Heat Deformation (100°C) ⁶	15	%	UL 1581
VW-1	Pass		UL 1581
Smoke Density			ASTM E662
Flame, 0.5 mm plaque, Ds, max	130		ASTM E662
Non-Flame, 0.5 mm plaque, Ds, max	130		ASTM E662
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.7E+15	ohms·cm	ASTM D257
Dielectric Strength (2.00 mm, in Oil)	20	kV/mm	IEC 60243-1
Dielectric Constant (1 MHz)	2.90		ASTM D150
Dissipation Factor (1 MHz)	4.0E-3		ASTM D150
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index (3.00 mm)	850	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (3.00 mm)	750	°C	IEC 60695-2-13
Oxygen Index	25	%	ISO 4589-2
Extrusion	Nominal Value	Unit	
Drying Temperature	75.0 - 85.0	°C	
Drying Time	5.0 - 7.0	hr	
Suggested Max Moisture	0.020	%	
Cylinder Zone 1 Temp.	180 - 220	°C	
Cylinder Zone 3 Temp.	220 - 250	°C	
Cylinder Zone 5 Temp.	220 - 250	°C	
Melt Temperature	220 - 250	°C	
Die Temperature	220 - 250	°C	
Extrusion instructions			
Conductor Pre-heat Temperature: 25 - 120 °CCooling Water Air Gap: 100 - 200 mmCross-head Temperature: 220 - 250 °CDrying Time (Cumulative): 12 hrsExtruder Length/Diameter Ratio (L/D): 22:1 to 26:1Neck Temperature: 220 - 250 °CScreen Pack: 150 - 100Screw Speed: 15 - 85 rpmWater Bath Temperature: 15 - 60 °C			
NOTE			
1.	Type 1, 50mm/min		
2.	After 7 days		
3.	Type 1, 50mm/min		
4.	After 7 days		
5.	13 mm/min		
6.	250 g		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

