

VICOTE® 708

Polyetheretherketone

Victrex plc

Message:

VICOTE 708 and 709 grades are specially developed powder coatings (based on VICTREX HT™ polymer) with a higher Tg and melting point than the standard VICOTE products. VICOTE 708 and 709 grades deliver extended high temperature performance while offering all the key characteristics of standard VICOTE Coatings. Key features of VICOTE 708 and 709 grades include:

- Retention of mechanical and physical properties at temperatures 30°C higher than other 700 series coatings.
- Up to 3 times the wear resistance of standard 700 series coatings.
- Higher levels of fatigue performance.
- Higher creep modulus than standard 700 series coatings at 150°C

VICOTE 708 and 709 grade powders are available in various average particle sizes from 10 - 50 microns. The powders are off-white in color and are available in various melt viscosities depending on the film thickness and level of melt flow required. Typical film thicknesses range from < 100 microns up to 500 microns.

VICOTE 708 and 709 grades, like other non-coating grades of VICTREX HT polymer, are thermoplastic in nature and exhibit flow above the melt temperature. When processed using the correct guidelines, the coatings will exhibit the excellent properties that VICTREX HT polymer is renowned for.

- High continuous use temperature of 260°C
- Excellent wear abrasion and cut through resistance at these high temperatures
- Excellent chemical and radiation resistance
- Low level of extractables
- Hydrolysis resistant
- Inherently flame retardant

General Information			
Features	Fatigue Resistant		
	Flame Retardant		
	Good Abrasion Resistance		
	Good Chemical Resistance		
	Good Wear Resistance		
	Hydrolysis Resistant		
	Low Extractables		
	Medium Heat Resistance		
	Radiation (Gamma) Resistant		
Uses	Coating Applications		
Agency Ratings	FDA 21 CFR 175.300		
Appearance	Off-White		
Forms	Powder		
Processing Method	Coating		
Physical	Nominal Value	Unit	Test Method
Density	1.32	g/cm³	ISO 1183
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	260	°C	Internal Method
Glass Transition Temperature	157	°C	DSC
Melting Temperature	374	°C	DSC
RTI Elec	260	°C	UL 746

RTI Imp	260	°C	UL 746
RTI Str	260	°C	UL 746
Extrusion	Nominal Value	Unit	
Drying Temperature	120 to 150	°C	
Drying Time	< 3.0	hr	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

