

Geon™ Vinyl Rigid Extrusion L8761

Rigid Polyvinyl Chloride

PolyOne Corporation

Message:

Geon™ Vinyl Rigid Extrusion L8761 is a rigid polyvinyl chloride product. It can be processed by extrusion and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Geon™ The application areas of Vinyl Rigid Extrusion L8761 include water pipes/pipes/drinking water and engineering/industrial accessories. The main characteristics are: chemical resistance.

General Information			
UL YellowCard	E41877-513904		
Features	Good chemical resistance		
Uses	Bar		
Agency Ratings	NSF 14		
	NSF 61		
	NSF Type I		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm ³	ASTM D792
PVC Cell Classification	12564		ASTM D1784
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	77		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	3060	MPa	ASTM D638
Tensile Strength ² (Yield)	55.4	MPa	ASTM D638
Flexural Modulus	3420	MPa	ASTM D790
Flexural Strength	98.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256A
Transverse flow: 23°C, 3.18mm, molded	48	J/m	ASTM D256A
Flow: 23°C, 3.18mm, molded	48	J/m	ASTM D256A
Drop Impact Resistance			ASTM D4226
23°C ³	63.6	J/cm	ASTM D4226
23°C ⁴	63.6	J/cm	ASTM D4226
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	71.7	°C	ASTM D648
CLTE - Flow	5.9E-5	cm/cm/°C	ASTM D696
Additional Information	Nominal Value		
Ease of Sizing	Good		

注释:按特定颜色获取NSF清单.请联系普立万公司获取该产品已认证颜色的最新清单.

Extrusion	Nominal Value	Unit
Melt Temperature	182 - 193	°C
NOTE		
1.	Type 1, 5.1 mm/min	
2.	Type 1, 5.1 mm/min	
3.	Procedure A, C.125 Throwing	
4.	Procedure B, C.125 Throwing	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

