

Strator® A-5 HTX

Polyamide 66

EPIC Polymers

Message:

STRATOR® A-5 HTX is a Polyamide 66 (Nylon 66) product filled with 50% long glass fiber. It is available in Europe. Primary characteristic: heat stabilizer.

General Information				
Filler / Reinforcement		Long Glass Fiber,50% Filler by Weight		
Additive		Heat Stabilizer		
Features		Heat Stabilized		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.58	--	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.20	--	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	1.3	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				ISO 527-2
23°C	17500	14000	MPa	
90°C	12500	--	MPa	
120°C	9100	--	MPa	
Tensile Stress				ISO 527-2
Yield, 23°C	265	215	MPa	
Yield, 90°C	220	--	MPa	
Yield, 120°C	150	--	MPa	
Tensile Strain (Break, 23°C)	2.4	--	%	ISO 527-2
Flexural Modulus (23°C)	14500	11300	MPa	ISO 178
Flexural Stress (23°C)	420	320	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	35	36	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	83	90	kJ/m ²	ISO 179
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	255	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	253	--	°C	ISO 75-2/A
CLTE - Flow (23°C)	2.0E-5	--	cm/cm/°C	ISO 7991
Thermal Conductivity	0.33	--	W/m/K	ISO 22007
Electrical	Dry	Conditioned	Unit	Test Method

Surface Resistivity	1.0E+12	--	ohms	ASTM D257
Electric Strength	36	--	kV/mm	IEC 60243-1
Comparative Tracking Index	500	--	V	IEC 60112
Extrusion	Dry	Unit		
Cylinder Zone 1 Temp.	270 to 300		°C	
Cylinder Zone 2 Temp.	270 to 300		°C	
Cylinder Zone 3 Temp.	285 to 310		°C	
Cylinder Zone 4 Temp.	285 to 320		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT