

LEXAN™ XHT4143 resin

Polycarbonate
SABIC Innovative Plastics

Message:

XHT4143 is a high flow, UV stabilized, high heat polycarbonate copolymer blend with an HDT/Af of 162C. It is available in a range of opaque and limited transparent colors.

General Information			
UL YellowCard	E121562-100321027		
Additive	UV Stabilizer		
Features	Copolymer		
	High Flow		
	High Heat Resistance		
Appearance	Clear/Transparent		
	Colors Available		
	Opaque		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.20	g/cm ³	ASTM D792
--	1.21	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (330°C/2.16 kg)	25	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (330°C/2.16 kg)	24.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.60 to 0.95	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	0.33	%	
Equilibrium, 23°C, 50% RH	0.25	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2730	MPa	ASTM D638
--	2750	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	77.0	MPa	ASTM D638
Yield	78.0	MPa	ISO 527-2/50
Break ³	69.0	MPa	ASTM D638
Break	67.0	MPa	ISO 527-2/50
Tensile Elongation			

Yield ⁴	7.0	%	ASTM D638
Yield	7.0	%	ISO 527-2/50
Break ⁵	50	%	ASTM D638
Break	50	%	ISO 527-2/50
Flexural Modulus			
50.0 mm Span ⁶	2600	MPa	ASTM D790
-- ⁷	2600	MPa	ISO 178
Flexural Stress			
--	80.0	MPa	ISO 178
Yield, 50.0 mm Span ⁸	120	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	9.0	kJ/m ²	
23°C	11	kJ/m ²	
Charpy Unnotched Impact Strength ¹⁰			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Notched Izod Impact			
-30°C	76	J/m	ASTM D256
23°C	93	J/m	ASTM D256
-30°C ¹¹	8.0	kJ/m ²	ISO 180/1A
23°C ¹²	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ¹³			ISO 180/1U
-30°C	No Break		
23°C	No Break		
Instrumented Dart Impact (23°C, Total Energy)	72.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	174	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ¹⁴	173	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	165	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹⁵	162	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	183	°C	ASTM D1525, ISO 306/B50 ¹¹ ¹⁶
--	181	°C	ISO 306/B120
Ball Pressure Test (165°C)	Pass		IEC 60695-10-2
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	6.0E-5	cm/cm/°C	
Transverse : -40 to 40°C	6.0E-5	cm/cm/°C	
Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index			IEC 60695-2-12

2.00 mm	850	°C
2.50 mm	960	°C
Injection	Nominal Value	Unit
Drying Temperature	135	°C
Drying Time	4.0 to 6.0	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	40 to 60	%
Rear Temperature	280 to 310	°C
Middle Temperature	290 to 310	°C
Front Temperature	300 to 315	°C
Nozzle Temperature	295 to 310	°C
Processing (Melt) Temp	300 to 315	°C
Mold Temperature	95.0 to 130	°C
Back Pressure	0.300 to 0.700	MPa
Screw Speed	40 to 90	rpm
Vent Depth	0.025 to 0.080	mm

NOTE

- 5.0 mm/min
- Type I, 50 mm/min
- Type I, 50 mm/min
- Type I, 50 mm/min
- Type I, 50 mm/min
- 1.3 mm/min
- 2.0 mm/min
- 1.3 mm/min
- 80*10*3 sp=62mm
- 80*10*3 sp=62mm
- 80*10*3
- 80*10*3
- 80*10*3
- 80*10*4 mm
- 80*10*4 mm
- Rate B (120°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

