

RTP 3505

Perfluoroethylene Propylene Copolymer

RTP Company

Message:

Glass Fiber

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.22	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.20 to 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6890	MPa	ASTM D638
Tensile Strength	33.1	MPa	ASTM D638
Tensile Elongation (Yield)	0.50 to 1.5	%	ASTM D638
Flexural Modulus	4140	MPa	ASTM D790
Flexural Strength	48.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	160	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	270	J/m	ASTM D4812
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 mm, ** Values per RTP Company testing.)	V-0	UL 94	
Additional Information	Nominal Value	Unit	
Primary Additive	30	%	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	343 to 385	°C	
Mold Temperature	93.3	°C	
Injection Pressure	20.7 to 55.2	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

