

APEL™ APL8008T

Cyclic Olefin Copolymer
Mitsui Chemicals America, Inc.

Message:

APEL™APL8008T is a cyclic olefin copolymer (COC) material. This product is available in North America.
Typical application areas include:
[sheet](#)
[Movie](#)

General Information			
Uses	Films		
	Sheet		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.02	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/2.16 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	50.0	MPa	ASTM D638
Tensile Elongation (Break)	100	%	ASTM D638
Flexural Modulus	2400	MPa	ASTM D790
Flexural Strength	90.0	MPa	ASTM D790
Films	Nominal Value	Unit	Test Method
Water Vapor Transmission Rate	0.090	g · mm/m ² /atm/24 hr	ASTM F1249
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	45	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	60.0	°C	ASTM D648
Glass Transition Temperature	70.0	°C	DSC
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.540		ASTM D542
Transmittance	91.0	%	ASTM D1003
Haze	2.0	%	ASTM D1003
Additional Information			

Unnotched Izod Impact, ASTM D256: 33 kJ/m²TMA: 80°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

