

Tufpet PBT G2030

Polybutylene Terephthalate
Mitsubishi Rayon America Inc.

Message:

Tufpet PBT G2030 is a polybutene terephthalate (PBT) material, which contains a 30% glass fiber reinforced material. This product is available in North America and is processed by injection molding.

The main features of Tufpet PBT G2030 are:

- flame retardant/rated flame
- Flame Retardant
- high gloss
- Good processability
- Good dimensional stability

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	Flame retardancy		
Features	Good dimensional stability		
	Highlight		
	Good formability		
	Good electrical performance		
	Good chemical resistance		
	Heat resistance, high		
	Low or no water absorption		
	Flame retardancy		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.65	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.10 - 0.90	%	ASTM D955
Water Absorption (Saturation, 23°C)	0.38	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	113	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	10300	MPa	ASTM D790
Flexural Strength	167	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
With Metal-Dynamic	0.10		ASTM D1894
With self-dynamics	0.21		ASTM D1894
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	76.0	mg	ASTM D1044

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	59	J/m	ASTM D256
Unnotched Izod Impact	540	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	220	°C	ASTM D648
1.8 MPa, not annealed	210	°C	ASTM D648
CLTE - Flow	5.0E-5	cm/cm/°C	ASTM D696
RTI Elec			UL 746
0.790 mm	130	°C	UL 746
1.57 mm	130	°C	UL 746
3.12 mm	130	°C	UL 746
5.59 mm	130	°C	UL 746
RTI Imp			UL 746
1.57 mm	115	°C	UL 746
3.12 mm	125	°C	UL 746
5.59 mm	125	°C	UL 746
RTI			UL 746
0.790 mm	130	°C	UL 746
1.57 mm	130	°C	UL 746
3.12 mm	130	°C	UL 746
5.59 mm	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.6E+18	ohms · cm	ASTM D257
Dielectric Constant (1 MHz)	3.30		ASTM D150
Dissipation Factor (1 MHz)	0.016		ASTM D150
Arc Resistance	12.0	sec	ASTM D495
Comparative Tracking Index (CTI)	250	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.790 mm	V-1		UL 94
1.57 mm	V-0		UL 94
3.12 mm	V-0		UL 94
5.59 mm	V-0		UL 94
Additional Information			
Coefficient of Linear Thermal Expansion, ASTM D696: 3 to 7 E-5 cm/cm/°C			
Injection	Nominal Value	Unit	
Drying Temperature	140	°C	
Drying Time	2.0	hr	
Rear Temperature	230 - 260	°C	
Middle Temperature	230 - 260	°C	
Front Temperature	230 - 260	°C	

Mold Temperature	40.0 - 100	°C
Injection Pressure	81.4	MPa
Screw Speed	80	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

