

Integra™ PC-5022 F1 FRA

Polycarbonate

PolySource, LLC

Message:

Flame Retardant, Medium Viscosity, UV Stabilized Polycarbonate

General Information			
UL YellowCard	E326789-100167740	E326789-100167741	E326789-100167742
Additive	UV stabilizer		
Features	UV Stabilized		
	Medium viscosity		
	Flame retardancy		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	15	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	62.1	MPa	ASTM D638
Tensile Elongation (Break)	75	%	ASTM D638
Flexural Modulus (23°C)	2210	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	89.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm)	530	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	137	°C	ASTM D648
1.8 MPa, not annealed	121	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.6 mm	V-0		UL 94
3.2 mm	5VA		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

