

# THERMOLAST® K TF3BNA (Series: FC/AP)

Thermoplastic Elastomer

KRAIBURG TPE

## Message:

- The FC/AP Series is your natural-colored and translucent material solution for applications with food contact. The series' features include an excellent adhesion to PP.
- Typical applications
  - Function and design elements
  - Grip applications
  - Household articles
  - Packaging (for food and careproducts)
  - Razors
  - Seals
  - Toothbrushes
  - Toys
  - Material advantages
  - Adhesion to PP
  - Applications with food contact
  - Easy coloring (compounds in natural colors)
  - EN71/3
  - Excellent mechanical properties
  - Excellent processing behavior
  - FDA compliant
  - Halogen-free
  - In natural or translucent available
  - Pleasant surface feel (Soft touch)
  - Recyclable
  - Regulation (EU) 10/2011

General Information	
Features	Food Contact Acceptable Good Adhesion Good Colorability Good Processability Halogen Free Recyclable Material Soft
Uses	Food Packaging Household Goods Non-specific Food Applications Packaging Seals Toothbrush Handles Toys
Agency Ratings	EN 71-3 EU 10/2011

## FDA Unspecified Rating

Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm <sup>3</sup>	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	29		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>1</sup> (Yield)	2.50	MPa	ISO 37
Tensile Elongation <sup>2</sup> (Break)	650	%	ISO 37
Tear Strength <sup>3</sup>	10	kN/m	ISO 34-1
Injection	Nominal Value	Unit	
Drying Temperature	60.0 to 80.0	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	180	°C	
Middle Temperature	200	°C	
Front Temperature	220	°C	
Mold Temperature	25.0 to 40.0	°C	
Injection Pressure	20.0 to 100	MPa	
Back Pressure	2.00 to 10.0	MPa	
NOTE			
1.	Type S2, 200 mm/min		
2.	Type S2, 200 mm/min		
3.	Method Bb, Angle (Nicked)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT