

TRIBOCOMP® PA66 CF30 TS12

Polyamide 66

EPIC Polymers

Message:

TRIBOCOMP® PA66 CF30 TS12 is a Polyamide 66 (Nylon 66) product filled with 30% carbon fiber. It is available in Europe. Primary characteristic: wear resistant.

General Information				
Filler / Reinforcement		Carbon Fiber,30% Filler by Weight		
Features		Good Wear Resistance		
		Low Friction		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.28	--	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.20	--	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	1.8	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				ISO 527-2
23°C	21000	16500	MPa	
90°C	14000	--	MPa	
120°C	10000	--	MPa	
Tensile Stress				ISO 527-2
Yield, 23°C	260	205	MPa	
Yield, 90°C	150	--	MPa	
Yield, 120°C	125	--	MPa	
Tensile Strain (Break, 23°C)	2.0	3.0	%	ISO 527-2
Flexural Modulus (23°C)	19000	--	MPa	ISO 178
Flexural Stress (23°C)	380	285	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	--	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	40	--	kJ/m ²	ISO 179
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	255	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	253	--	°C	ISO 75-2/A
CLTE - Flow (23°C)	2.1E-5	--	cm/cm/°C	ISO 7991
Thermal Conductivity	0.51	--	W/m/K	ISO 22007

Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+2	--	ohms	ASTM D257
Extrusion	Dry	Unit		
Cylinder Zone 1 Temp.	270 to 300		°C	
Cylinder Zone 2 Temp.	275 to 295		°C	
Cylinder Zone 3 Temp.	280 to 295		°C	
Cylinder Zone 4 Temp.	290 to 310		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT