

POLYfill PPH Q15030 E10

Polypropylene Homopolymer

Polykemi AB

Message:

Mineral reinforced Elastomer modified

General Information			
Filler / Reinforcement	Mineral,30% Filler by Weight		
Additive	Impact Modifier		
Features	Impact Modified		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.90 to 1.1	%	
Flow	0.90 to 1.1	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	35.0	MPa	ISO 527-2
Tensile Strain (Yield)	8.0	%	ISO 527-2
Flexural Modulus (23°C)	2600	MPa	ISO 178
Flexural Stress	60.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹			
0.45 MPa, Unannealed	135	°C	ISO 75-2/B
1.8 MPa, Unannealed	77.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	144	°C	ISO 306/A50
--	80.0	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Ignition Temperature (2.00 mm)	750	°C	IEC 60695-2-13
NOTE			
1.	120°C/hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

