

Infino VB-5300G

Polybutylene Terephthalate

SAMSUNG SDI CO., LTD.

Message:

Infino VB-5300G is a Polybutylene Terephthalate (PBT) product filled with glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

General Information			
UL YellowCard	E115797-219686	E115797-219690	
Filler / Reinforcement	Glass Fiber		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.63	g/cm³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	15	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.30 to 0.90	%	ASTM D955, ISO 2577
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
R-Scale	120		ASTM D785
R-Scale	119		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	7700	MPa	ASTM D638
--	7600	MPa	ISO 527-2/50
Tensile Strength			
Yield ²	130	MPa	ASTM D638
Yield	150	MPa	ISO 527-2/50
Break ³	130	MPa	ASTM D638
Break	150	MPa	ISO 527-2/50
Tensile Elongation			
Break ⁴	3.0	%	ASTM D638
Break	4.0	%	ISO 527-2/50
Flexural Modulus			
-- ⁵	8800	MPa	ASTM D790
-- ⁶	8800	MPa	ISO 178
Flexural Strength			
-- ⁷	190	MPa	ASTM D790
-- ⁸	210	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	10	kJ/m²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.18 mm	74	J/m	ASTM D256

23°C, 6.35 mm	69	J/m	ASTM D256
23°C ¹⁰	10	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 6.40 mm	222	°C	ASTM D648
0.45 MPa, Unannealed, 4.00 mm	221	°C	ISO 75-2/B
1.8 MPa, Unannealed, 6.40 mm	210	°C	ASTM D648
1.8 MPa, Unannealed, 4.00 mm	206	°C	ISO 75-2/A
Vicat Softening Temperature	210	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature			
--	100	°C	
Desiccant Dryer	100	°C	
Drying Time			
--	4.0 to 6.0	hr	
Desiccant Dryer	2.0 to 4.0	hr	
Suggested Max Moisture	< 0.050	%	
Rear Temperature	210 to 220	°C	
Middle Temperature	225 to 230	°C	
Front Temperature	240 to 250	°C	
Nozzle Temperature	250	°C	
Mold Temperature	60.0 to 120	°C	
Injection Pressure	49.0 to 245	MPa	
Back Pressure	0.490 to 1.96	MPa	
Screw Speed	50 to 150	rpm	
NOTE			
1.	5.0 mm/min		
2.	5.0 mm/min		
3.	5.0 mm/min		
4.	5.0 mm/min		
5.	2.8 mm/min		
6.	2.0 mm/min		
7.	2.8 mm/min		
8.	2.0 mm/min		
9.	Thickness: 4 mm		
10.	Thickness: 4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

