

LNP™ LUBRICOMP™ OFL36A compound

Branched Polyphenylene Sulfide

SABIC Innovative Plastics

Message:

LNP LUBRICOMP OFL36A is a compound based on PPS - Branched resin containing 30% Glass Fiber, 15% PTFE. Added features of this material include: Wear Resistant.

Also known as: LNP* LUBRICOMP* Compound OFL-4036

Product reorder name: OFL36A

General Information			
UL YellowCard	E121562-101283823		
Filler / Reinforcement	Carbon Fiber,30% Filler by Weight		
Additive	PTFE Lubricant (15%)		
Features	Branched Polymer Structure		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.69	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.10 to 0.20	%	ASTM D955
Across Flow : 24 hr	0.30 to 0.50	%	ASTM D955
Across Flow : 24 hr	0.30 to 0.48	%	ISO 294-4
Flow : 24 hr	0.13 to 0.18	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.040	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	12300	MPa	ASTM D638
--	11100	MPa	ISO 527-2/1
Tensile Strength			
Break	145	MPa	ASTM D638
Break	124	MPa	ISO 527-2
Tensile Elongation			
Break	1.7	%	ASTM D638
Break	1.4	%	ISO 527-2
Flexural Modulus	11000	MPa	ASTM D790, ISO 178
Flexural Strength			
--	200	MPa	ASTM D790
--	197	MPa	ISO 178
Coefficient of Friction			ASTM D3702 Modified

vs. Itself - Dynamic	0.44		
vs. Itself - Static	0.35		
Wear Factor - Washer	33.0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	85	J/m	ASTM D256
23°C ²	9.4	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	550	J/m	ASTM D4812
23°C ³	26	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	3.40	J	ASTM D3763
--	1.97	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	269	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	266	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	2.3E-5	cm/cm/°C	ASTM E831
Flow : -40 to 40°C	2.4E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	4.9E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	5.0E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0	hr	
Rear Temperature	304 to 316	°C	
Middle Temperature	321 to 332	°C	
Front Temperature	332 to 343	°C	
Processing (Melt) Temp	316 to 321	°C	
Mold Temperature	138 to 166	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

