

Infino CF-1021T

Polycarbonate

LOTTE ADVANCED MATERIALS CO., LTD.

Message:

Infino CF-1021T is a polycarbonate (PC) product. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: electrical/electronic applications.

General Information			
UL YellowCard	E115797-102870766		
Features	General		
Uses	Mobile phone		
Physical	Nominal Value	Unit	Test Method
Specific Gravity (Natural)	1.18	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238, ISO 1133
250°C/10.0 kg	36	g/10 min	ASTM D1238, ISO 1133
300°C/1.2 kg	19	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow: 3.20mm	0.50 - 0.51	%	ASTM D955
Transverse flow: 3.20mm	0.54 - 0.55	%	ASTM D955
Lateral flow: 3.20mm	0.54 - 0.55	%	ISO 2577
Traffic: 3.20mm	0.50 - 0.51	%	ISO 2577
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
Class r	120		ASTM D785
R scale	120		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2200	MPa	ASTM D638
--	2200	MPa	ISO 527-2/50
Tensile Strength			
Yield ²	64.0	MPa	ASTM D638
Yield	60.0	MPa	ISO 527-2/50
Fracture ³	69.0	MPa	ASTM D638
Fracture	75.0	MPa	ISO 527-2/50
Tensile Elongation			
Fracture ⁴	80	%	ASTM D638
Fracture	80	%	ISO 527-2/50
Flexural Modulus			
-- ⁵	2100	MPa	ASTM D790
-- ⁶	2300	MPa	ISO 178

Flexural Strength			
-- 7	83.0	MPa	ASTM D790
-- 8	92.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	57	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.18 mm	690	J/m	ASTM D256
23°C, 6.35 mm	98	J/m	ASTM D256
23°C ¹⁰	70	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 6.40mm	133	°C	ASTM D648
0.45 MPa, unannealed, 4.00mm	133	°C	ISO 75-2/B
1.8 MPa, unannealed, 6.40mm	120	°C	ASTM D648
1.8 MPa, not annealed, 4.00mm	130	°C	ISO 75-2/A
Vicat Softening Temperature	140	°C	ISO 306/B50
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	50 mm/min		
5.	2.8 mm/min		
6.	2.0 mm/min		
7.	2.8 mm/min		
8.	2.0 mm/min		
9.	Thickness: 4mm		
10.	Thickness: 4mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT