

Fireguard® 910L16-C14-NL

Flexible Polyvinyl Chloride

Teknor Apex Company

Message:

Fireguard®910L16-C14-NL is a flexible polyvinyl chloride material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

Fireguard®The main features of 910L16-C14-NL are:

ROHS certification

Flame Retardant

Typical application areas include:

Wire and cable

Electrical/electronic applications

General Information			
Features	Low smoke		
	Flame retardancy		
Uses	Ceiling compartment cable sheath material		
Wire Types	CL2P		
	CL3P		
	CMP		
	FPLP		
	MPP		
	OFNP		
Agency Ratings	NEC Article 725		
	NEC Article 760		
	NEC Article 770		
	NEC Article 800		
	UL 13		
	UL 1424		
	UL 1651		
	UL 444		
RoHS Compliance	UL QMTM2 .E200337		
	RoHS compliance		
Appearance	Opacity		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.63	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240

Shaw C	92		ASTM D2240
Shaw C, 10 seconds	87		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	17.2	MPa	ASTM D638
Tensile Elongation (Break)	240	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	75.0	°C	ASTM D794
Brittleness Temperature	-10.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant			ASTM D150
1 kHz	4.37		ASTM D150
1 MHz	3.61		ASTM D150
Dissipation Factor			ASTM D150
1 kHz	0.061		ASTM D150
1 MHz	0.039		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	50	%	ASTM D2863
Additional Information			
Av.Sp. 消光面积:148 平方米/千克平均燃烧热:8.99 兆焦/千克平均放热速率:53 千瓦/平方米动态热稳定性, 205°C,100 rpm,72 gms:40Kayeness ACR,370°F,1000 秒-1:362 帕-秒峰值放热速率:75 千瓦/平方米峰值烟雾量:0.93 1/mTA六位说明编号130-927总放热率:56 兆焦/平方米			
Extrusion	Nominal Value	Unit	
Melt Temperature	196	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

