

PRL PPX-MF-FR3

Polyphenylene Ether + PS

Polymer Resources Ltd.

Message:

PRL PPX-MF-FR3 is a Polyphenylene Ether + PS (PPE+PS) product filled with mineral. It can be processed by injection molding and is available in North America.

Characteristics include:

- Flame Rated
- RoHS Compliant
- Flame Retardant
- Halogen Free
- Heat Resistant

General Information			
UL YellowCard	E113219-219263		
Filler / Reinforcement	Mineral		
Additive	Flame Retardant		
Features	Bromine Free		
	Chlorine Free		
	Flame Retardant		
	Medium Heat Resistance		
	Self Extinguishing		
RoHS Compliance	RoHS Compliant		
UL File Number	E113219		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/11.6 kg)	3.0 to 10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.18 mm	72.4	MPa	
Break, 3.18 mm	58.6	MPa	
Tensile Elongation			ASTM D638
Yield, 3.18 mm	3.5	%	
Break, 3.18 mm	8.0	%	
Flexural Modulus (3.18 mm)	3450	MPa	ASTM D790
Flexural Strength (Break, 3.18 mm)	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.4	kJ/m ²	ISO 179/2C

Notched Izod Impact			
23°C, 3.18 mm	110	J/m	ASTM D256
23°C	8.4	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	110	°C	
1.8 MPa, Unannealed, 3.18 mm	104	°C	
Vicat Softening Temperature	127	°C	ASTM D1525 ¹
RTI Elec			UL 746
1.50 mm	65.0	°C	
3.00 mm	65.0	°C	
RTI Imp			UL 746
1.50 mm	65.0	°C	
3.00 mm	65.0	°C	
RTI Str			UL 746
1.50 mm	65.0	°C	
3.00 mm	65.0	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		
3.00 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	104 to 110	°C	
Drying Time	3.0 to 4.0	hr	
Drying Time, Maximum	8.0	hr	
Rear Temperature	249 to 299	°C	
Middle Temperature	260 to 304	°C	
Front Temperature	271 to 310	°C	
Processing (Melt) Temp	288 to 316	°C	
Mold Temperature	71.1 to 93.3	°C	
NOTE			
1.	Rate B (120°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

