

Sindustris PP TE5008B

Polypropylene

Sincerity Australia Pty Ltd.

Message:

Sindustris PP TE5008B is a Polypropylene material. It is available in Asia Pacific for injection molding.

Important attributes of Sindustris PP TE5008B are:

Good Weather Resistance

Impact Modified

Impact Resistant

Typical application of Sindustris PP TE5008B: Automotive

General Information			
Additive	Rubber		
Features	Good Weather Resistance		
	High Impact Resistance		
	Low Density		
Uses	Automotive Bumper		
	Automotive Exterior Parts		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.90 to 1.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	14.7	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	400	%	ASTM D638
Flexural Modulus ³ (6.40 mm)	7350	MPa	ASTM D790
Flexural Strength ⁴ (6.40 mm)	15.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-10°C, 6.40 mm	98	J/m	
23°C, 6.40 mm	No Break		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.20 mm)	85.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	
Drying Time	3.0 to 4.0	hr	

Suggested Max Moisture	0.010	%
Rear Temperature	190 to 210	°C
Middle Temperature	200 to 230	°C
Front Temperature	200 to 230	°C
Nozzle Temperature	210 to 230	°C
Processing (Melt) Temp	200 to 230	°C
Mold Temperature	40.0 to 60.0	°C
Back Pressure	29.4 to 58.8	MPa
Screw Speed	30 to 60	rpm

NOTE

- | | |
|----|-----------|
| 1. | 50 mm/min |
| 2. | 50 mm/min |
| 3. | 10 mm/min |
| 4. | 10 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

