

LEXAN™ SLX2571T resin

Polycarbonate

SABIC Innovative Plastics Europe

Message:

Transparent weatherable PC copolymer for blowmolding/extrusion.

General Information			
UL YellowCard	E45329-102354900		
Features	Copolymer		
	Good weather resistance		
RoHS Compliance	RoHS compliance		
Appearance	Clear/transparent		
Processing Method	Extrusion blow molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	3.0	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	2.70	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.60 - 0.80	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.35	%	ISO 62
Equilibrium, 23°C, 50% RH	0.15	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2400	MPa	ASTM D638
--	2360	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	62.0	MPa	ASTM D638
Yield	63.0	MPa	ISO 527-2/50
Fracture ³	64.0	MPa	ASTM D638
Fracture	63.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	7.5	%	ASTM D638
Yield	6.0	%	ISO 527-2/50
Fracture ⁵	110	%	ASTM D638
Fracture	98	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2400	MPa	ASTM D790
-- ⁷	2250	MPa	ISO 178

Flexural Stress			
--	94.7	MPa	ISO 178
Yield, 50.0mm span ⁸	101	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	15	kJ/m ²	ISO 179/1eA
23°C	75	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ¹⁰ (23°C)	No Break		ISO 179/1eU
Notched Izod Impact			
-30°C	140	J/m	ASTM D256
23°C	850	J/m	ASTM D256
-30°C ¹¹	10	kJ/m ²	ISO 180/1A
23°C ¹²	70	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ¹³ (23°C)	No Break		ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	74.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	126	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹⁴	125	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	143	°C	ASTM D1525, ISO 306/B50 ¹⁵
--	145	°C	ISO 306/B120
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	6.0E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	6.4E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm, Testing by SABIC)	V-2		UL 94
Extrusion	Nominal Value	Unit	
Drying Temperature	116 - 121	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.020	%	
Cylinder Zone 1 Temp.	260 - 274	°C	
Cylinder Zone 2 Temp.	260 - 274	°C	
Cylinder Zone 3 Temp.	260 - 274	°C	
Cylinder Zone 4 Temp.	260 - 274	°C	
Cylinder Zone 5 Temp.	260 - 274	°C	
Adapter Temperature	260 - 274	°C	
Die Temperature	268 - 279	°C	
Extrusion instructions			

Drying Time (Cumulative): 48 hrsHead - Zone 6 - Top Temperature: 260 - 274 °CHead - Zone 7 - Bottom Temperature: 260 - 274 °CMelt Temperature (Parison): 266 - 277 °CMinimum Moisture Content: 0.01 %Mold Temperature: 66 - 93 °CScrew Speed: 15 - 50 rpm

NOTE

1.	5.0 mm/min
2.	Type 1, 50mm/min
3.	Type 1, 50mm/min
4.	Type 1, 50mm/min
5.	Type 1, 50mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*3 sp=62mm
10.	80*10*3 sp=62mm
11.	80*10*3
12.	80*10*3
13.	80*10*3
14.	80*10*4 mm
15.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT