

Nordbak Locking Compound

Epoxy; Epoxide

Loctite®

Message:

Nordbak Locking Compound is an Epoxy; Epoxide (Epoxy) product. It is available in North America.

Characteristics include:

Flame Retardant

Heat Resistant

Impact Resistant

General Information			
Features	Flame Retardant		
	Good Impact Resistance		
	High Heat Resistance		
Uses	Machinery Maintenance/Repair		
Appearance	Grey		
Forms	Pellets		
Hardness	Nominal Value		Test Method
Durometer Hardness (Shore D)	90		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	41.4	MPa	ASTM D638
Compressive Strength	82.7	MPa	ASTM D695
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	107	°C	ASTM D794
Thermoset	Nominal Value	Unit	
Pot Life (25°C)	10	min	
Demold Time (25°C)	480	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT