

Maxxam™ PP FR 7380-8001

Polypropylene
PolyOne Corporation

Message:
Polypropylene, flame retardant and low blooming

General Information			
Features	Flame retardancy		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.02	g/cm ³	ASTM D792
Molding Shrinkage	1.6 - 1.8	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	25.0	MPa	ASTM D638
Tensile Elongation ² (Break)	200	%	ASTM D638
Flexural Modulus ³	1300	MPa	ASTM D790
Flexural Strength ⁴	35.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	100	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 3.20mm	105	°C	ASTM D648
1.8 MPa, not annealed	90.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		Internal method
Glow Wire Flammability Index	875	°C	IEC 60695-2-12
Glow Wire Ignition Temperature	875	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 85.0	°C	
Drying Time	4.0 - 6.0	hr	
Processing (Melt) Temp	200 - 240	°C	
Mold Temperature	30.0 - 60.0	°C	
Injection instructions			
Injection Pressure: MED-HIGHHold Pressure: MED-HIGHScrew Speed: MODERATEBack Pressure: LOW			
NOTE			
1.	50 mm/min		
2.	50 mm/min		

3.	1.3 mm/min
4.	1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

