

Exceed™ 1012 MK mVLDPE

Metallocene Polyethylene Resin
ExxonMobil Chemical

Message:

EXCEED 1012 MK resin is a metallocene ethylene-hexene copolymer. Films made from Exceed 1012MK mVLDPE resins have outstanding cold temperature toughness, impact strength and puncture. These superior strength properties, along with excellent heat sealing and hot tack performance, make this a very versatile packaging film resin.

General Information			
Additive	Processing aid		
	Anti-caking agent (5000 ppm)		
	heat stabilizer		
	Sliding agent (1000 ppm)		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
1% secant, MD	119	MPa	ASTM D882
1% secant, TD	133	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield	7.03	MPa	ASTM D882
TD: Yield	7.36	MPa	ASTM D882
MD: Fracture	54.7	MPa	ASTM D882
TD: Fracture	48.1	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	460	%	ASTM D882
TD: Fracture	580	%	ASTM D882
Dart Drop Impact	1000	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD	210	g	ASTM D1922
TD	330	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	45		ASTM D2457
Haze	15	%	ASTM D1003
Legal statement			

本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT