

Ultradur® B 4300 G2 High Speed

Polybutylene Terephthalate

BASF Corporation

Message:

Easy flowing injection molding grade with 10 % glass fibers; for rigid, tough and dimensionally stable technical parts (eg timer dials, toggles, knobs, parts for thermostats, oven-door handles, toaster housings and grills).

General Information			
UL YellowCard	E36632-101116595	E41871-100048461	E36632-531667
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Good Dimensional Stability		
	Good Flow		
	Good Toughness		
	High Rigidity		
Uses	Appliance Components		
	Engineering Parts		
	Handles		
	Housings		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PBT-GF10		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm ³	ISO 1183
Apparent Density	0.70 to 0.80	g/cm ³	
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	28.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.1	%	
Flow	0.90	%	
Water Absorption			ISO 62
Saturation, 23°C	0.40	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Viscosity Number ¹	105	cm ³ /g	ISO 307

Mold Shrinkage ²			
free, longitudinal	0.59	%	
free, transverse	1.3	%	
Maximum Service Temperature - short cycle operation	210	°C	
Automotive Materials (> 1.00 mm)	Passed		FMVSS 302
Screw Speed	< 250	mm/sec	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4400	MPa	ISO 527-2
Tensile Stress (Break)	85.0	MPa	ISO 527-2
Tensile Strain (Break)	3.9	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	26	kJ/m ²	
23°C	25	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	210	°C	ISO 75-2/B
1.8 MPa, Unannealed	165	°C	ISO 75-2/A
Melting Temperature	223	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms · cm	IEC 60093
Relative Permittivity			IEC 60250
100 Hz	3.60		
1 MHz	3.60		
Dissipation Factor			IEC 60250
100 Hz	1.2E-3		
1 MHz	0.015		
Comparative Tracking Index (Solution A)	300	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification (1.60 mm)	HB		IEC 60695-11-10, -20
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 120	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.040	%	
Hopper Temperature	80.0	°C	
Rear Temperature	250	°C	
Middle Temperature	255	°C	
Front Temperature	260	°C	
Nozzle Temperature	260	°C	

Processing (Melt) Temp	230 to 275	°C
Mold Temperature	60.0 to 100	°C
NOTE		
1.	solution 0,005 g/ml Phenole/1,2 Dichlorbenzol 1:1	
2.	plate with film gate 150*150*3 mm ³	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

