

LNP™ THERMOCOMP™ JF004E compound

Polyethersulfone
SABIC Innovative Plastics

Message:

LNP THERMOCOMP JF004E is a compound based on Polyethersulfone resin containing Glass Fiber. Added features of this material include: Easy Molding.
Also known as: LNP* THERMOCOMP* Compound JF-1004 EM
Product reorder name: JF004E

General Information			
UL YellowCard	E207780-101283849		
Filler / Reinforcement	Glass fiber reinforced material		
Features	Good formability		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.51	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.50 - 0.70	%	ASTM D955
Transverse flow: 24 hours	0.60 - 0.80	%	ASTM D955
Vertical flow direction: 24 hours	0.60 - 0.80	%	ISO 294-4
Flow direction: 24 hours	0.50 - 0.70	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.40	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	7360	MPa	ASTM D638
--	7590	MPa	ISO 527-2/1
Tensile Strength			
Fracture	114	MPa	ASTM D638
Fracture	109	MPa	ISO 527-2
Tensile Elongation (Break)	2.9	%	ASTM D638, ISO 527-2
Flexural Modulus			
--	6690	MPa	ASTM D790
--	7590	MPa	ISO 178
Flexural Strength			
--	186	MPa	ASTM D790
--	183	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	59	J/m	ASTM D256
23°C ²	7.1	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	430	J/m	ASTM D4812
23°C ³	73	kJ/m ²	ISO 180/1U

Instrumented Dart Impact			
23°C, Energy at Peak Load	16.0	J	ASTM D3763
--	4.00	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	206	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁴	205	°C	ISO 75-2/Af
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

