

Crastin® SK601 BK851

THERMOPLASTIC POLYESTER RESIN

DuPont Performance Polymers

Message:

10% Glass Reinforced Polybutylene Terephthalate

General Information			
UL YellowCard	E41938-257817		
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Processing Method	Injection Molding		
Part Marking Code (ISO 11469)	>PBT-GF10<		
Resin ID (ISO 1043)	PBT-GF10		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4500	MPa	ISO 527-2
Tensile Stress (Break)	90.0	MPa	ISO 527-2
Tensile Strain (Break)	4.0	%	ISO 527-2
Flexural Stress	140	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	35	kJ/m ²	
23°C	35	kJ/m ²	
Notched Izod Impact Strength (23°C)	4.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	180	°C	ISO 75-2/A
Melting Temperature ¹	225	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification (1.50 mm)	HB		IEC 60695-11-10, -20
Oxygen Index	20	%	ISO 4589-2
Additional Information	Nominal Value	Unit	Test Method
Emission of Organic Compounds	72.0	µgC/g	VDA 277
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT