

# VESTAMID® L LX9008

Polyamide 12  
Evonik Industries AG

Message:

Unfilled polyamid 12 compounds  
Characterization: high viscosity, highly heat stabilized  
Application Examples: diesel fuel lines  
The properties of PA 12 compounds can be modified to suit the requirements of many applications by incorporating various additives such as stabilizers, plasticizers, reinforcements, and fillers.  
The VESTAMID® L compounds of Evonik comprise a range of various products that are customized to the requirements of processors and users. Many of the PA 12 compounds are suitable especially for the injection molding of recision parts; others have been developed specifically for the extrusion process.

General Information			
Additive	Heat Stabilizer		
Features	Fatigue Resistant		
	Food Contact Acceptable		
	Fuel Resistant		
	Good Abrasion Resistance		
	Good Impact Resistance		
	Good Processability		
	Grease Resistant		
	Heat Stabilized		
	High ESCR (Stress Crack Resist.)		
	High Viscosity		
	Low to No Water Absorption		
	Oil Resistant		
	Solvent Resistant		
	Sound Damping		
	Vibration Damping		
Uses	Fuel Lines		
Agency Ratings	EU 10/2011		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.01	g/cm³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	1.9	%	
Flow	0.25	%	
Water Absorption			ISO 62
Saturation, 23°C	1.4	%	
Equilibrium, 23°C, 50% RH	0.70	%	
Mechanical	Nominal Value	Unit	Test Method

Tensile Modulus	1450	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	42.0	MPa	
Break	48.0	MPa	
Tensile Strain			ISO 527-2
Yield	5.0	%	
Break	> 50	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C, Complete Break	22	kJ/m <sup>2</sup>	
23°C, Complete Break	45	kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	125	°C	ISO 75-2/B
1.8 MPa, Unannealed	45.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	175	°C	ISO 306/A
--	145	°C	ISO 306/B
Melting Temperature <sup>1</sup>	176	°C	ISO 11357-3
CLTE - Flow (23 to 55°C)	1.4E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Electric Strength	26	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.70		
23°C, 1 MHz	2.90		
Dissipation Factor			IEC 60250
23°C, 100 Hz	0.052		
23°C, 1 MHz	0.032		
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
Additional Information	Nominal Value		Test Method
ISO Shortname	PA12, EHL, 22-010		ISO 1874
NOTE			
1.	2nd Heating		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

