

EXCELINK 1600B

Thermoplastic Vulcanizate

JSR Corporation

Message:

EXCELINK 1600B is a thermoplastic vulcanized rubber (TPV) material. This product is available in North America or Asia Pacific region. The processing method is injection molding.

The main features of EXCELINK 1600B are:

Strong adhesion

high liquidity

Good processability

Typical application areas include:

Sealing applications

Automotive Industry

General Information			
Features	Good formability		
	Good adhesion		
	High liquidity		
Uses	Seals		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.880	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
230°C/2.16 kg	0.80	g/10 min	ISO 1133
230°C/5.0 kg	43	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	56		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress - Across Flow			ISO 37
100% strain	1.60	MPa	ISO 37
300% strain	2.30	MPa	ISO 37
Tensile Stress - Across Flow (Yield)	4.80	MPa	ISO 37
Tensile Elongation - Across Flow (Break)	640	%	ISO 37
Compression Set			ISO 815
23°C, 22 hr	37	%	ISO 815
70°C, 22 hr	48	%	ISO 815
Optical	Nominal Value		Test Method
Gloss (60°)	44		ISO 2813
Additional Information			
Adhesive Strength, JSR Method, 200 mm/min: 1.9 MPaAdhesive Elongation, JSR Method, 200 mm/min: 130%			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

