

LNP™ STAT-KON™ FX98500C compound

Polyethylene

SABIC Innovative Plastics

Message:

LNP STAT-KON FX98500C is a compound based on Polyethylene resin containing Proprietary Filler(s). Added feature of this material is: Electrically Conductive.

Also known as: LNP* STAT-KON* Compound PDX-F-98500

Product reorder name: FX98500C

General Information			
Filler / Reinforcement	Proprietary		
Features	Electrically Conductive		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.976	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955, ISO 294-4
Flow : 24 hr	2.7 to 3.0	%	
Across Flow : 24 hr	1.9 to 2.2	%	
Water Absorption			
24 hr, 50% RH	0.020	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.020	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	1080	MPa	ASTM D638
--	871	MPa	ISO 527-2/1
Tensile Strength			
Yield	23.9	MPa	ASTM D638
Yield	23.0	MPa	ISO 527-2
Break	13.9	MPa	ASTM D638
Break	14.0	MPa	ISO 527-2
Tensile Elongation			
Yield	16	%	ASTM D638
Yield	14	%	ISO 527-2
Break	43	%	ASTM D638
Break	83	%	ISO 527-2
Flexural Modulus			
--	870	MPa	ASTM D790
--	931	MPa	ISO 178
Flexural Strength			
--	26.5	MPa	ASTM D790
--	27.0	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	48	J/m	ASTM D256
23°C ²	5.8	kJ/m ²	ISO 180/1A
Unnotched Izod Impact (23°C)	No Break		ASTM D4812, ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	21.4	J	ASTM D3763
--	63.2	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	46.7	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ³	48.0	°C	ISO 75-2/Af
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+5	ohms	ASTM D257
Volume Resistivity	1.0E+2 to 1.0E+5	ohms·cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Rear Temperature	193 to 204	°C	
Middle Temperature	210 to 221	°C	
Front Temperature	221 to 232	°C	
Processing (Melt) Temp	232	°C	
Mold Temperature	37.8 to 54.4	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT