

VITAMIDE® AS10BK6603

Polyamide 66

Jackdaw Polymers

Message:

VITAMIDE® AS10BK6603 is a Polyamide 66 (Nylon 66) product. It is available in Europe. Primary characteristic: flame rated.

General Information			
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage	1.5	%	Internal Method
Water Absorption			
24 hr	1.5	%	ASTM D570
23°C, 24 hr	1.5	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	75.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	30	%	ASTM D638, ISO 527-2
Flexural Modulus	2800	MPa	ASTM D790, ISO 178
Flexural Stress			
--	105	MPa	ISO 178
Break	105	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.5	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break		ISO 179
Notched Izod Impact Strength	5.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	190	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	70.0	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature	> 230	°C	ISO 306/B50
Melting Temperature	260	°C	ISO 1218, ASTM D2117
CLTE - Flow	7.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257, IEC 60093
Dielectric Strength	28	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-2		UL 94
Oxygen Index	27	%	ASTM D2863, ISO 4589-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

