

Celanex® 3309HRHF

Polybutylene Terephthalate

Celanese Corporation

Message:

Celanex 3309HRHF is a 30% fiberglass reinforced Polybutylene Terephthalate which has excellent hydrolysis resistance, mechanical properties and improved flow.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Good liquidity		
	Hydrolysis resistance		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.53	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Vertical flow direction	0.70 - 1.2	%	ISO 294-4
Flow direction	0.10 - 0.30	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.16	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10400	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	150	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	2.6	%	ISO 527-2/1A/5
Flexural Modulus (23°C)	9700	MPa	ISO 178
Flexural Stress (23°C)	220	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	9.1	kJ/m ²	ISO 179/1eA
23°C	8.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	39	kJ/m ²	ISO 179/1eU
23°C	44	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	9.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	45	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	222	°C	ISO 75-2/B
1.8 MPa, not annealed	210	°C	ISO 75-2/A
Melting Temperature ¹	225	°C	ISO 11357-3

Linear thermal expansion coefficient			ISO 11359-2
Flow	1.9E-5	cm/cm/°C	ISO 11359-2
Lateral	1.0E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.0E+15	ohms	IEC 60093
Volume Resistivity	2.0E+17	ohms·cm	IEC 60093
Dielectric Strength	22	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	2.80		IEC 60250
1 MHz	3.20		IEC 60250
Dissipation Factor (1 MHz)	0.014		IEC 60250
Comparative Tracking Index	254	V	IEC 60112
Injection	Nominal Value	Unit	
Suggested Max Regrind	25	%	
Rear Temperature	230 - 240	°C	
Middle Temperature	235 - 250	°C	
Front Temperature	240 - 260	°C	
Nozzle Temperature	250 - 260	°C	
Processing (Melt) Temp	235 - 260	°C	
Mold Temperature	65.0 - 93.0	°C	
Injection Rate	Fast		
Back Pressure	0.00 - 0.345	MPa	
Injection instructions			
Screw Speed: Medium			
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

