

apinat® DP2125

Biodegradable Polymers

API SpA

Message:

apinat®DP2125 is a biodegradable polymer (Biodeg Polymers) product. It is available in Europe. The main features are: environmental protection/green.

General Information			
Features	Updatable resources		
	Biodegradable		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15 - 1.18	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	60		ASTM D2240
Shaw D	40		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2.70 - 14.0	MPa	ASTM D638
Tensile Elongation (Break)	410 - 790	%	ASTM D638
Abrasion Resistance	37.0 - 250	mm ³	DIN 53516
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	22.0 - 107	kN/m	ASTM D624
Injection	Nominal Value	Unit	
Rear Temperature	110 - 130	°C	
Middle Temperature	120 - 140	°C	
Front Temperature	120 - 140	°C	
Nozzle Temperature	120 - 145	°C	
Mold Temperature	25.0 - 40.0	°C	
Injection Rate	Slow-Moderate		
Injection instructions			
Injection Pressure: MediumBack Pressure: Medium/Low			
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	90.0 - 110	°C	
Cylinder Zone 2 Temp.	110 - 125	°C	
Cylinder Zone 3 Temp.	125 - 150	°C	
Cylinder Zone 4 Temp.	130 - 160	°C	
Cylinder Zone 5 Temp.	135 - 155	°C	
Extrusion instructions			
L/D ratio: 24:1Compression Screw Ratio: 2.3:1Screw Speed: 50 rpm			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

