

AIE PA66 60G6

Polyamide 66

Asia International Enterprise (Hong Kong) Limited

Message:

AIE PA66 60G6 is a Polyamide 66 (Nylon 66) material filled with 30% glass fabric. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of AIE PA66 60G6 are:

Flame Rated

High Flow

General Information			
UL YellowCard	E252275-476080		
Filler / Reinforcement	Glass Fabric,30% Filler by Weight		
Features	High Flow		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.39	g/cm ³	ISO 1183
Molding Shrinkage	0.30 to 0.60	%	Internal Method
Water Absorption (23°C, 24 hr)	1.7	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	230	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	9100	MPa	ISO 178
Flexural Stress	310	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	24	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	260	°C	ISO 75-2/B
1.8 MPa, Unannealed	250	°C	ISO 75-2/A
Melting Temperature (DSC)	265	°C	ISO 3146
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	240 to 270	°C	
Mold Temperature	50.0 to 100	°C	
Injection Pressure	30.0 to 80.0	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

