

Bergamid™ B70 G30 H Black UV

Polyamide 6

PolyOne Corporation

Message:

Bergamid B70 G30 H Black UV is a Polyamide 6 (Nylon 6) product filled with 30% glass fiber. It can be processed by injection molding and its features are heat and UV stabilized.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good UV Resistance		
	Heat Stabilized		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9500	MPa	ISO 527-2
Tensile Strength	180	MPa	ISO 527
Tensile Strain (Break)	3.5	%	ISO 527
Flexural Strength	250	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	8.0	kJ/m ²	
23°C	10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	80	kJ/m ²	
23°C	90	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	< 220	°C	ISO 75-2/B
1.8 MPa, Unannealed	< 210	°C	ISO 75-2/A
Continuous Use Temperature	110	°C	IEC 216
Melting Temperature (DSC)	215 to 225	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms · cm	IEC 60093
Electric Strength	80	kV/mm	IEC 60243-1
Relative Permittivity	3.80		IEC 60250

Dissipation Factor	0.023		IEC 60250
Comparative Tracking Index	500	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	250 to 280	°C	
Mold Temperature	50.0 to 90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

