

Durethan® BKV 215 H3.0 000000

Polyamide Copolymer

LANXESS GmbH

Message:

PA 6-Copolymer, 15 % glass fibers, injection molding, improved impact strength, heat-aging stabilized

General Information				
UL YellowCard		E245249-560482		
Filler / Reinforcement		Glass Fiber,15% Filler by Weight		
Additive		Heat Stabilizer		
Features		Good Impact Resistance		
		Heat Stabilized		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.18	--	g/cm ³	ISO 1183
Apparent Density	0.60	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Across Flow : 280°C, 3.00 mm ¹	0.83	--	%	
Across Flow : 120°C, 4 hr, 3.00 mm ²	0.15	--	%	
Flow : 280°C, 3.00 mm ³	0.30	--	%	
Flow : 120°C, 4 hr, 3.00 mm ⁴	0.050	--	%	
Water Absorption				ISO 62
Saturation, 23°C	7.0	--	%	
Equilibrium, 23°C, 50% RH	2.0	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	4500	2300	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	85.0	50.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	4.5	15	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	4200	2300	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% Strain,23°C	125	55.0	MPa	
23°C ⁶	135	75.0	MPa	
Flexural Strain at Flexural Strength ⁷ (23°C)	5.5	8.5	%	ISO 178/A
ISO Shortname	PA 6/66-HI, GHR, 14-040, GF15--			ISO 1874
Residual Moisture Content	0.030 to 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method

Charpy Notched Impact Strength				ISO 179/1eA
-30°C	10	12	kJ/m ²	
23°C	20	35	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	80	80	kJ/m ²	
23°C	70	95	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A
-30°C	10	10	kJ/m ²	
23°C	20	35	kJ/m ²	
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	65	60	kJ/m ²	
23°C	60	90	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	205	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	175	--	°C	ISO 75-2/A
Vicat Softening Temperature	200	--	°C	ISO 306/B120
Melting Temperature ⁸	214	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	4.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	1.7E-4	--	cm/cm/°C	
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	HB	--		
3.20 mm	HB	--		
Oxygen Index ⁹	22	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	260 to 290		°C	
Mold Temperature	80.0 to 100		°C	
NOTE				
1.	150x105x3mm, 80°C MT, 400 bar			
2.	150x105x3mm			
3.	150x105x3mm, 80°C MT, 400 bar			
4.	150x105x3mm			

5.	2.0 mm/min
6.	2.0 mm/min
7.	2 mm/min
8.	10°C/min
9.	Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

