

Durethan® AKV 35 HR H2.0 901510

Polyamide 66

LANXESS Corporation

Message:

PA 66, 35 % glass fibers, injection molding, heat-aging stabilized, hydrolysis stabilized

General Information				
Filler / Reinforcement		Glass Fiber,35% Filler by Weight		
Additive		Heat Stabilizer		
		Hydrolysis Resistant		
Features		Good Heat Aging Resistance		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity				
--	1.41	--	g/cm ³	ASTM D792
23°C	1.41	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 300°C, 2.00 mm ¹	1.1	--	%	
Across Flow : 120°C, 2 hr, 2.00 mm ²	0.090	--	%	
Flow : 300°C, 2.00 mm ³	0.38	--	%	
Flow : 120°C, 2 hr, 2.00 mm ⁴	0.060	--	%	
Water Absorption				ISO 62
Saturation, 23°C	5.2	--	%	
Equilibrium, 23°C, 50% RH	1.7	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				
23°C ⁵	11000	6090	MPa	ASTM D638
23°C	11500	7800	MPa	ISO 527-2/1
Tensile Strength				
Break, 23°C	190	--	MPa	ASTM D638
Break, 23°C	195	135	MPa	ISO 527-2/5
Tensile Elongation				
Break, 23°C	3.0	--	%	ASTM D638
Break, 23°C	3.1	6.0	%	ISO 527-2/5
Flexural Modulus				
23°C	10000	--	MPa	ASTM D790

23°C ⁶	10700	7000	MPa	ISO 178/A
Flexural Strength				
23°C	290	--	MPa	ASTM D790
3.5% Strain ⁷	--	180	MPa	ISO 178/A
23°C ⁸	305	210	MPa	ISO 178
Flexural Strain at Flexural Strength ⁹ (23°C)	3.8	6.0	%	
Burning Behavior ¹⁰ (> 1.00 mm)	passed	--		ISO 3795
ISO Shortname	PA 66, GHRW, 14-110, GF30	--		ISO 1874
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-40°C	< 10	< 10	kJ/m ²	
-30°C	< 10	< 10	kJ/m ²	
23°C	13	20	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	75	80	kJ/m ²	
23°C	85	85	kJ/m ²	
Notched Izod Impact				
23°C, 3.18 mm	140	--	J/m	ASTM D256
-30°C	10	10	kJ/m ²	ISO 180/1A
23°C	< 10	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	65	--	kJ/m ²	
23°C	75	--	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed, 3.99 mm	> 249	--	°C	ASTM D648
0.45 MPa, Unannealed	250	--	°C	ISO 75-2/B
1.8 MPa, Unannealed, 3.99 mm	> 249	--	°C	ASTM D648
1.8 MPa, Unannealed	245	--	°C	ISO 75-2/A
Vicat Softening Temperature				
--	> 230	--	°C	ISO 306/B50
--	255	--	°C	ISO 306/B120
Melting Temperature ¹¹	262	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	2.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	8.0E-5	--	cm/cm/°C	

Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+12	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	1.0E+12	ohms·cm	IEC 60093
Electric Strength				IEC 60243-1
23°C, 1.00 mm	35	--	kV/mm	
23°C, 3.00 mm	40	35	kV/mm	
Dielectric Constant				IEC 60250
23°C, 50 Hz ¹²	4.00	10.0		
23°C, 1 MHz ¹³	4.00	4.00		
23°C, 100 Hz	3.90	--		
23°C, 1 MHz	3.60	--		
Dissipation Factor				IEC 60250
23°C, 50 Hz	6.0E-3	1.0		
23°C, 100 Hz	0.010	--		
	0.015			
23°C, 1 MHz	4.0E-3	0.18		
Comparative Tracking Index (Solution A)	425	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	HB	--		
3.20 mm	HB	--		
Glow Wire Flammability Index (2.00 mm)	650	--	°C	IEC 60695-2-12
Oxygen Index ¹⁴	26	--	%	ISO 4589-2
Injection	Dry	Unit		
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	280 to 300		°C	
Mold Temperature	80.0 to 120		°C	
NOTE				
1.	60x60x2; MT 80°C; 600 Bar			
2.	60x60x2			
3.	60x60x2; MT 80°C; 600 Bar			
4.	60x60x2			
5.	1.0 mm/min			
6.	2.0 mm/min			
7.	2.0 mm/min			
8.	2.0 mm/min			
9.	Pull Rate: 2 mm/min; 50% RH			

10.	US-FMVSS302
11.	10°C/min
12.	Tinfoil Electrodes
13.	Tinfoil Electrodes
14.	Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

