

XAREC™ N WA 5030

Syndiotactic Polystyrene + Nylon

Idemitsu Kosan Co., Ltd.

Message:

XAREC™ N WA 5030 is a Syndiotactic Polystyrene + Nylon (SPS+Nylon) product filled with 30% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
UL File Number	E48268		
Physical	Nominal Value	Unit	Test Method
Density	1.35	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow	0.30 to 0.60	%	
Flow	0.20 to 0.40	%	
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	0.19	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10000	MPa	ISO 527-2
Tensile Stress (Break)	165	MPa	ISO 527-2
Tensile Strain (Break)	2.4	%	ISO 527-2
Flexural Modulus	9400	MPa	ISO 178
Flexural Stress	235	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	11	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	47	kJ/m ²	ISO 179
Notched Izod Impact Strength (23°C)	10	kJ/m ²	ISO 180
Unnotched Izod Impact Strength (23°C)	40	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ²			
0.45 MPa, Unannealed	260	°C	ISO 75-2/B
1.8 MPa, Unannealed	245	°C	ISO 75-2/A
CLTE			TMA
Flow : -30 to 30°C	2.3E-5	cm/cm/°C	
Transverse : -30 to 30°C	4.3E-5	cm/cm/°C	
RTI Elec	50.0	°C	UL 746
RTI Imp	50.0	°C	UL 746
RTI Str	50.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	7.4E+15	ohms · cm	IEC 60093
Dielectric Strength	22	kV/mm	ASTM D149

Dielectric Constant (1 MHz)	3.30	IEC 60250	
Dissipation Factor (1 MHz)	0.034	IEC 60250	
Arc Resistance	PLC 5	ASTM D495	
Comparative Tracking Index (CTI) ³	PLC 2	IEC 60112	
High Amp Arc Ignition (HAI)		UL 746	
1.50 mm	PLC 0		
3.00 mm	PLC 0		
Hot-wire Ignition (HWI)		UL 746	
1.50 mm	PLC 4		
3.00 mm	PLC 4		
Flammability	Nominal Value	Unit	Test Method
Flame Rating (> 1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	80.0	°C	
Drying Time - Desiccant Dryer	1.0 to 3.0	hr	
Processing (Melt) Temp	280 to 310	°C	
Mold Temperature	50.0 to 80.0	°C	
NOTE			
1.	24h		
2.	Mold temperature: 80°C		
3.	Solution A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

