

# Wellamid® MR410 22H-WBK

Polyamide 66  
Wellman Engineering Resins

Message:

Wellamid® MR410 22H-WBK is a Polyamide 66 (Nylon 66) material filled with 40% mineral. It is available in Asia Pacific, Europe, Latin America, or North America. Primary attribute of Wellamid® MR410 22H-WBK: Good Weather Resistance.

| General Information                               |                              |                   |             |
|---------------------------------------------------|------------------------------|-------------------|-------------|
| Filler / Reinforcement                            | Mineral,40% Filler by Weight |                   |             |
| Features                                          | Good Weather Resistance      |                   |             |
| Appearance                                        | Black                        |                   |             |
| Forms                                             | Pellets                      |                   |             |
| Physical                                          | Nominal Value                | Unit              | Test Method |
| Density                                           | 1.48                         | g/cm <sup>3</sup> | ISO 1183    |
| Molding Shrinkage                                 |                              |                   | ISO 294-4   |
| Across Flow : 23°C                                | 1.0 to 1.4                   | %                 |             |
| Flow : 23°C                                       | 0.80 to 1.2                  | %                 |             |
| Mechanical                                        | Nominal Value                | Unit              | Test Method |
| Tensile Stress (Yield, 23°C)                      | 75.0                         | MPa               | ISO 527-2   |
| Tensile Strain (Yield, 23°C)                      | 4.0                          | %                 | ISO 527-2   |
| Flexural Modulus (23°C)                           | 7200                         | MPa               | ISO 178     |
| Flexural Stress (23°C)                            | 130                          | MPa               | ISO 178     |
| Impact                                            | Nominal Value                | Unit              | Test Method |
| Notched Izod Impact Strength (23°C)               | 4.0                          | kJ/m <sup>2</sup> | ISO 180     |
| Thermal                                           | Nominal Value                | Unit              | Test Method |
| Heat Deflection Temperature (1.8 MPa, Unannealed) | 165                          | °C                | ISO 75-2/A  |
| Melting Temperature (DSC)                         | 260                          | °C                | ISO 3146    |
| Injection                                         | Nominal Value                | Unit              |             |
| Drying Temperature                                | 79.4                         | °C                |             |
| Drying Time                                       | 2.0 to 4.0                   | hr                |             |
| Suggested Max Moisture                            | 0.20                         | %                 |             |
| Rear Temperature                                  | 282 to 304                   | °C                |             |
| Middle Temperature                                | 277 to 299                   | °C                |             |
| Front Temperature                                 | 271 to 293                   | °C                |             |
| Nozzle Temperature                                | 282 to 293                   | °C                |             |
| Processing (Melt) Temp                            | 288 to 310                   | °C                |             |
| Mold Temperature                                  | 71.1 to 93.3                 | °C                |             |
| Injection Pressure                                | 34.5 to 138                  | MPa               |             |
| Back Pressure                                     | 0.345                        | MPa               |             |
| Screw Speed                                       | 30 to 120                    | rpm               |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

