

HANWHA CCBA-8735BK

Polyolefin

Hanwha Chemical

Message:

Hanwha Wire and Cable Compound CCBA-8735BK is a semiconductive compound for insulation shielding of medium voltage(33kV) power cables. CCBA-8735BK has a low adhesion level in the range 2~4kg/0.5inch.

General Information			
Features	Semi-conductive		
	Good electrical performance		
	Excellent appearance		
Uses	Cable guard		
	Wire and cable applications		
	Medium voltage insulation		
Agency Ratings	AEIC CS5		
	AEIC CS7		
	BS 6622		
	ICEA S-66-524 NEMA WC 7		
	IEC 60502		
	IEC 60840		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.17	g/cm ³	ASTM D1505
Moisture Content		ppm	Karl Fisher
Peel Strength	1.5	kN/m	ASTM D903
Oven Aging (136°C)	7.0	day	
Tensile strength retention-7 days (136°C)	> 90	%	ASTM D638
Elongation retention rate-7 days (136°C)	> 85	%	ASTM D638
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	13.7	MPa	ASTM D638
Tensile Elongation (Break)	300	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-50.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity			ASTM D257
23°C	< 5.0E+2	ohms · cm	ASTM D257

90°C	< 1.0E+3	ohms·cm	ASTM D257
Extrusion	Nominal Value	Unit	
Melt Temperature	100 - 110	°C	
Extrusion instructions			

Cure Temperature : 320~390°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

