

GAZOLE™ 6430CF

Polybenzimidazole
Gharda Chemicals Ltd.

Message:

Product Details: Ultra high performance thermoplastic polymer, 30% Carbon fiber reinforced in AB- PBI/PEK Blend, semi-crystalline granules suitable for injection molding as well as extrusion, easy flow, dark green in color.

Application Areas: Suitable for high temperature applications under extreme high load, Excellent wear resistance, suitable for semiconductor applications and plasma handling equipments.

General Information			
Filler / Reinforcement	Carbon Fiber,30% Filler by Weight		
Features	Good Flow		
	Good Wear Resistance		
	Semi Crystalline		
Uses	Electrical/Electronic Applications		
	High Temperature Applications		
Appearance	Dark Green		
Forms	Granules		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	
Molding Shrinkage ¹			
Flow	0.0	%	
Across Flow	0.20	%	
Water Absorption (Equilibrium)	0.23	%	ASTM D570
Spiral Flow ²	3.70	cm	ASTM D3123
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	95		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	28500	MPa	ASTM D638
Tensile Strength (Yield, 23°C)	230	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.7	%	ASTM D638
Flexural Modulus (23°C)	28800	MPa	ASTM D790
Flexural Strength (23°C)	380	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	45	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	358	°C	ASTM D648
Continuous Use Temperature	300	°C	UL 746B
Glass Transition Temperature	152	°C	ASTM D3418
Melting Temperature	372	°C	ASTM D3418
Flammability	Nominal Value		Test Method
Flame Rating (0.800 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	150	°C	
Drying Time	4.0 to 6.0	hr	
Hopper Temperature	60.0 to 80.0	°C	
Nozzle Temperature	445	°C	
Processing (Melt) Temp	400 to 445	°C	
Mold Temperature	200 to 220	°C	
NOTE			
1.	445°C nozzle, 220°C Mold		
2.	445°C nozzle, 220°C Mold		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

