

ESTOPLAST MG 7035NN02

Polybutylene Terephthalate
Ester Industries Ltd.

Message:

Polyethylene Terephthalate - 35% Glass Filled, Natural
Automotive: Ignition coil bobbin & Housing, Carburator Parts

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 35% filler by weight		
Additive	Nucleating agent demoulding		
Features	Nucleated Good demoulding performance		
Uses	Application in Automobile Field Shell spool		
RoHS Compliance	RoHS compliance		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.62	g/cm ³	ASTM D792
Water Absorption			ISO 62
Saturated, 23°C	0.45	%	ISO 62
Equilibrium, 23°C, 50% RH	0.18	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	150	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Strength	255	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	90	J/m	ASTM D256
Unnotched Izod Impact	800	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	245	°C	ASTM D648
1.8 MPa, not annealed	240	°C	ASTM D648
Flammability	Nominal Value		Test Method

Flame Rating (1.5 mm)	HB	UL 94
Injection	Nominal Value	Unit
Drying Temperature	105 - 115	°C
Drying Time	3.0 - 4.0	hr
Rear Temperature	270 - 280	°C
Middle Temperature	270 - 290	°C
Nozzle Temperature	270 - 285	°C
Processing (Melt) Temp	270 - 290	°C
Mold Temperature	110 - 130	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

