

LEXAN™ EXL9132 resin

Polycarbonate

SABIC Innovative Plastics Asia Pacific

Message:

Opaque PC-Siloxane copolymer with excellent processability. Improved flow, low temperature ductility, UV stabilized. Non-chlorinated, non-brominated flame retardant product. UL rated V0/5VA.

General Information			
Additive	UV stabilizer		
Features	Chlorine Free		
	Copolymer		
	Workability, good		
	Good liquidity		
	Bromine-free		
	ductility		
	Flame retardancy		
RoHS Compliance	RoHS compliance		
Appearance	Opacity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.18	g/cm ³	ASTM D792
--	1.19	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	17	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	16.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal method
Flow: 3.20mm	0.40 - 0.80	%	Internal method
Transverse flow: 3.20mm	0.40 - 0.80	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.35	%	ISO 62
Equilibrium, 23°C, 50% RH	0.15	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	95.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2270	MPa	ASTM D638
--	2200	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	58.1	MPa	ASTM D638

Yield	59.0	MPa	ISO 527-2/50
Fracture ³	58.5	MPa	ASTM D638
Fracture	55.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	5.8	%	ASTM D638
Yield	5.0	%	ISO 527-2/50
Fracture ⁵	100	%	ASTM D638
Fracture	100	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2340	MPa	ASTM D790
-- ⁷	2300	MPa	ISO 178
Flexural Stress			
--	88.0	MPa	ISO 178
Yield, 50.0mm span ⁸	95.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	25	kJ/m ²	ISO 179/1eA
23°C	60	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ¹⁰			ISO 179/1eU
-30°C	No Break		ISO 179/1eU
23°C	No Break		ISO 179/1eU
Notched Izod Impact			
-30°C	560	J/m	ASTM D256
23°C	730	J/m	ASTM D256
-30°C ¹¹	20	kJ/m ²	ISO 180/1A
23°C ¹²	55	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ¹³			ISO 180/1U
-30°C	No Break		ISO 180/1U
23°C	No Break		ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	67.9	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	136	°C	ASTM D648
0.45 MPa, unannealed, 100 mm span ¹⁴	136	°C	ISO 75-2/Be
1.8 MPa, unannealed, 3.20mm	124	°C	ASTM D648
1.8 MPa, unannealed, 100 mm span ¹⁵	124	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	143	°C	ASTM D1525, ISO 306/B50 10 ¹⁶
--	144	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			

Flow: -40 to 40°C	7.2E-5	cm/cm/°C	ASTM E831
Flow: 23 to 80°C	7.5E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	7.2E-5	cm/cm/°C	ASTM E831
Lateral: 23 to 80°C	7.5E-5	cm/cm/°C	ISO 11359-2
RTI Elec	130	°C	UL 746
RTI Imp	50.0	°C	UL 746
RTI	50.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (3.20 mm, in Oil)	19	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
50 Hz	2.70		IEC 60250
60 Hz	2.70		IEC 60250
1 MHz	2.70		IEC 60250
Dissipation Factor			IEC 60250
50 Hz	4.0E-4		IEC 60250
60 Hz	4.0E-4		IEC 60250
1 MHz	0.010		IEC 60250
Comparative Tracking Index	175	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		UL 94
3.00 mm	5VA		UL 94
Glow Wire Flammability Index (1.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.00 mm)	825	°C	IEC 60695-2-13
Oxygen Index	40	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	217 - 293	°C	
Middle Temperature	282 - 304	°C	
Front Temperature	293 - 316	°C	
Nozzle Temperature	288 - 310	°C	
Processing (Melt) Temp	293 - 316	°C	
Mold Temperature	71.0 - 93.0	°C	
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	40 - 70	rpm	
Vent Depth	0.025 - 0.076	mm	
NOTE			
1.	50 mm/min		

2.	Type 1, 50mm/min
3.	Type 1, 50mm/min
4.	Type 1, 50mm/min
5.	Type 1, 50mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*3 sp=62mm
10.	80*10*3 sp=62mm
11.	80*10*3
12.	80*10*3
13.	80*10*3
14.	120*10*4 mm
15.	120*10*4 mm
16.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

