

Ekalon® 26 E I V

Polycarbonate

Sattler KunststoffWerk GmbH

Message:

Ekalon® 26 E I V is a polycarbonate (PC) product. It is available in Europe.

Features include:

flame retardant/rated flame

Flame Retardant

low viscosity

mold release agent

excellent release agent

General Information			
Additive	demoulding		
Features	Low viscosity		
	Good demoulding performance		
	Flame retardancy		
UL File Number	E178422		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.24	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	26	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction: 23°C	0.20 - 0.60	%	ISO 294-4
Flow direction: 23°C	0.30 - 0.80	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2200	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/10
Yield, 23°C	55.0	MPa	ISO 527-2/10
Fracture, 23°C	38.0	MPa	ISO 527-2/10
Tensile Strain			ISO 527-2/10
Yield, 23°C	4.0	%	ISO 527-2/10
Fracture, 23°C	50	%	ISO 527-2/10
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	135	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-2		UL 94
3.00 mm	V-2		UL 94

Glow Wire Flammability Index			IEC 60695-2-12
1.00 mm	900	°C	IEC 60695-2-12
2.00 mm	960	°C	IEC 60695-2-12

Additional Information

Density, ISO 1183: 1.18 to 1.3 g/cm³Melt Mass-Flow Rate, ISO 1133, 300°C/1.2 kg: 23 to 29 g/10minNeedle Flame Test, DIN EN 60695-2-2, 1.5mm: 30 s

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

