

Kepital® TE-22

Acetal (POM) Copolymer

Korea Engineering Plastics Co., Ltd

Message:

A medium viscosity grade for general injection molding. It was modified with elastomer, and suitable for parts requiring higher impact resistance and toughness.

General Information			
UL YellowCard	E120354-220466		
Features	Good Toughness		
	High Impact Resistance		
	Medium Viscosity		
Uses	General Purpose		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
190°C/2.16 kg	8.0	g/10 min	ASTM D1238
--	8.5	g/10 min	ISO 1133
Molding Shrinkage			
Flow : 2.00 mm	1.5	%	
3.00 mm	1.8	%	
Water Absorption (Equilibrium, 23°C, 60% RH)	0.23	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield, 23°C	46.0	MPa	ASTM D638
Yield, 23°C	51.0	MPa	ISO 527-2
Tensile Elongation (Break)	220	%	ASTM D638
Nominal Tensile Strain at Break	> 50	%	ISO 527-2
Flexural Modulus			
23°C	1860	MPa	ASTM D790
23°C	1900	MPa	ISO 178
Flexural Strength			
23°C	65.0	MPa	ASTM D790
23°C	68.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	11	kJ/m ²	ISO 179/1eA

Notched Izod Impact (3.20 mm)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed	95.0	°C	ASTM D648
1.8 MPa, Unannealed	76.0	°C	ISO 75-2/A
Peak Melting Temperature	165	°C	ASTM D3418
CLTE - Flow (20 to 80°C)	1.3E-4	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257, IEC 60093
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257, IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

