

Tenopom® POM B3 M3 NTLA014 PR301

Acetal (POM) Copolymer

Petropol Industry and Trade of Polymers LTDA

Message:

Polyacetal copolymer, lubricated with molybdenum disulfide, recommended in cases where it is desired characteristics of sliding. Suitable for injection

General Information			
Additive	Molybdenum Disulfide Lubricant		
Features	Copolymer		
	Lubricated		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	>POM<		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40 to 1.44	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	25 to 28	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.8 to 2.0	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	61.0	MPa	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	2600	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	60	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.35 mm	160	°C	
1.8 MPa, Unannealed, 6.35 mm	100	°C	
Peak Melting Temperature	170	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Dissipation Factor (1 MHz)	6.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	180 to 200	°C	
Mold Temperature	70.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

