

SKYGREEN® KN100

Polyethylene Terephthalate Glycol Comonomer

SK Chemicals

Message:

SKYGREEN® KN100 is a Polyethylene Terephthalate Glycol Comonomer (PETG) material. It is available in Asia Pacific, Europe, or North America.

General Information			
Physical	Nominal Value	Unit	Test Method
Density	1.27	g/cm ³	ASTM D1505
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Water Absorption (24 hr)	0.13	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	108		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield ¹	50.0	MPa	ASTM D638
Yield	50.0	MPa	ISO 527-2/50
Break ²	29.0	MPa	ASTM D638
Break	29.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ³	4.5	%	ASTM D638
Yield	4.5	%	ISO 527-2/50
Break ⁴	180	%	ASTM D638
Break	180	%	ISO 527-2/50
Flexural Modulus ⁵	2100	MPa	ASTM D790, ISO 178
Flexural Strength ⁶	69.0	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	110	J/m	ASTM D256
23°C	12	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	70.0	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	62.0	°C	ASTM D648, ISO 75-2/A
Optical	Nominal Value	Unit	Test Method
Transmittance	90.0	%	ASTM D1003
Haze	< 1.0	%	ASTM D1003
NOTE			
1.	50 mm/min		
2.	50 mm/min		

3.	50 mm/min
4.	50 mm/min
5.	1.3 mm/min
6.	1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

