

Starex GR-5030FX

Styrene Acrylonitrile

SAMSUNG SDI CO., LTD.

Message:

Starex GR-5030FX is a Styrene Acrylonitrile (SAN) product filled with glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: flame rated.

General Information			
UL YellowCard	E115797-219794		
Filler / Reinforcement	Glass Fiber		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	5.5	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow : 3.20 mm	0.10 to 0.20	%	ASTM D955
Across Flow : 3.20 mm	0.16 to 0.20	%	ISO 2577
Flow : 3.20 mm	0.12 to 0.14	%	ISO 2577
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	8100	MPa	ASTM D638
--	8000	MPa	ISO 527-2/50
Tensile Strength			
Yield ²	110	MPa	ASTM D638
Yield	120	MPa	ISO 527-2/50
Break ³	120	MPa	ASTM D638
Break	120	MPa	ISO 527-2/50
Tensile Elongation			
Break ⁴	2.0	%	ASTM D638
Break	2.0	%	ISO 527-2/50
Flexural Modulus			
-- ⁵	9000	MPa	ASTM D790
-- ⁶	11000	MPa	ISO 178
Flexural Strength			
-- ⁷	130	MPa	ASTM D790
-- ⁸	170	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	5.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact			

23°C, 3.18 mm	54	J/m	ASTM D256
23°C ¹⁰	5.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed, 4.00 mm	113	°C	ISO 75-2/B
1.8 MPa, Unannealed, 6.40 mm	104	°C	ASTM D648
1.8 MPa, Unannealed, 4.00 mm	108	°C	ISO 75-2/A
Vicat Softening Temperature	112	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
--	HB		
3.00 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature			
--	80.0	°C	
Desiccant Dryer	80.0	°C	
Drying Time			
--	4.0 to 6.0	hr	
Desiccant Dryer	2.0 to 4.0	hr	
Suggested Max Moisture	< 0.050	%	
Rear Temperature	180 to 190	°C	
Middle Temperature	200 to 210	°C	
Front Temperature	220 to 230	°C	
Nozzle Temperature	230	°C	
Mold Temperature	40.0 to 60.0	°C	
Injection Pressure	93.2	MPa	
Back Pressure	0.490 to 1.96	MPa	
Screw Speed	50 to 150	rpm	
NOTE			
1.	5.0 mm/min		
2.	5.0 mm/min		
3.	5.0 mm/min		
4.	5.0 mm/min		
5.	2.8 mm/min		
6.	2.0 mm/min		
7.	2.8 mm/min		
8.	2.0 mm/min		
9.	Thickness: 4 mm		
10.	Thickness: 4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT