

MAJORIS AFR992 - 8229

Polypropylene Copolymer

AD majoris

Message:

AFR992 - 8229 is a halogen free flame retardant compound UL 94 V0, intended for extrusion and blow moulding.

AFR992 - 8229 produce very low level of toxicity and low smoke density in the case of a fire.

General Information			
Additive	Flame Retardant		
Features	Copolymer		
	Flame Retardant		
	Halogen Free		
	Low Smoke Emission		
	Low Toxicity		
	Recyclable Material		
Forms	Pellets		
Processing Method	Blow Molding		
	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.02	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/5.0 kg)	3.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1140	MPa	ISO 527-2/1
Tensile Stress (Yield)	22.0	MPa	ISO 527-2/50
Tensile Strain (Break)	> 300	%	ISO 527-2/50
Flexural Modulus ¹	1610	MPa	ISO 178
Flexural Stress	42.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	21	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Glow Wire Flammability Index (1.00 mm)	960	°C	IEC 60695-2-12
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	180 to 190	°C	
Cylinder Zone 3 Temp.	180 to 190	°C	
Cylinder Zone 5 Temp.	180 to 190	°C	
Melt Temperature	200	°C	

Head Temperature	200	°C
Die Temperature	200	°C
NOTE		
1.	2.0 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

